

DESCOR® Translucent

Fields of application

.01 .02 .04 .05 .06 .07 .11

Specifications



599189 173



100 % polyester
knit fabrics
PVC-free, recyclable



ca. 155/ 252/ 310/ 505 cm
ca. 61/ 99/ 122/ 199 inch
other widths available on request



B-s1, d0 DIN EN 13501-1



ca. 205 g/m²
ca. 6.1 oz/yd²



ca. 0.36 mm
ca. 360 µm



rolls
50/ 100 m
55/ 109 yd



blank: 5
DIN EN ISO 105-B02



blank: 35.7 %
DIN EN 410



blank: 93.7
DIN 5033-1



length: 2.2 %
cross: 0.9 %
DIN EN 14704-1



indirect, direct light



cold, ultrasonic cut



length: 290.7 N
cross: 1119.3 N
DIN EN ISO 13934-1 - max. tensile strength



length: 65.4 %
cross: 34.0 %
DIN EN ISO 13934-1 - max. tensile elongation



length: 26.1 N
cross: 13.7 N
DIN EN ISO 13937-2 - trouser tear propagation

Printing methods

print	UV	Latex	Dyesub	UVgel
Inside	•	•		
Outside				

Certifications



DESCOR® Translucent

Fields of application

.01 .02 .04 .05 .06 .07 .11



Ref.-Nr.: 599189 173 | Preview print sample